

Exciton states in cylindrical nanowires

A. F. Slachmuylders,^{1,*} B. Partoens,^{1,†} W. Magnus,^{2,1,‡} and F. M. Peeters^{1,§}

¹*Departement Fysica, Universiteit Antwerpen, Groenenborgerlaan 171, B-2020 Antwerpen, Belgium*

²*Interuniversity Microelectronics Centre, Kapeldreef 75, B-3001 Leuven, Belgium*

The exciton ground state and excited state energies are calculated for a model system of an infinitely long cylindrical wire. The effective Coulomb potential between the electron and the hole is studied as function of the wire radius. Within the adiabatic approximation, we obtain ‘exact’ numerical results for the effective exciton potential and the lowest exciton energy levels which are fitted to simple analytical expressions. Furthermore, we investigated the influence of a magnetic field parallel to the nanowire on the effective potential and the exciton energy.

PACS numbers: 71.35.-y, 78.67.Lt

I. INTRODUCTION

Nowadays, semiconductor nanowires with a small diameter can be realized in a fast and cost effective manner. One of the possible growth techniques, the VLS (vapor-liquid-solid) technique, is a bottom-up technique which appears to be very promising¹. In this method, a liquid metal cluster acts as a catalyst where reactants dissolve, which leads to the direct growth from the supersaturated alloy droplet. This growth method results in a freestanding nanowire that is not surrounded by any other material, in contrast to the embedded wires.

From a theoretical point of view such semiconductor nanowire structures are very interesting for understanding the role of dimensionality on physical properties. Furthermore, they provide a great potential for several applications, such as transistors², diodes³, memory elements⁴, lasers^{5,6}, chemical and biological sensors⁷, etc.

These nanowires have a large aspect ratio and can be considered one-dimensional structures. They have a length and a diameter in the micrometer resp. nanometer range. Electrons and holes are strongly confined in two directions and there is no confinement in the direction of the axis of the wire. Here we will investigate the exciton binding energy and its lowest excited states. Excitons form the basis of optical properties reflecting the intrinsic nature of low-dimensional systems. As a first step we investigate the potential and energy of the electron-hole pair. Because our aim is to present numerical ‘exact’ results we will limit ourselves for the moment, to the *model* system in which the difference in dielectric constant of the nanowire material and its surrounding is neglected. Only in this special case we are able to present analytical results. Although for ‘stand alone’ nanowires the dielectric mismatch in the wire (difference in dielectric constant of the material of the wire and the environment) is important, the study of it will be postponed for further investigations.

In previous work⁸, a similar model system was studied, but only the ground exciton state was obtained and no systematic study was presented of the dependence on wire radius, mass of the carriers, magnetic field and of the excited states. Also impurity states – both with and

without a magnetic field parallel to the wire axis – were considered in previous papers^{9,10}, with the charged impurity fixed to the cylinder axis and with averaging performed only over the electronic motion. Furthermore, the effective potential for the ground state configuration was calculated before¹¹ and perfectly fits our results. But the aim of the present paper is to give a more general result with different analytical expressions for the effective Coulomb potential that are fitted to the numerical results. These fits haven’t been given before and provide us with a tool which is extremely useful for further numerical calculations. Furthermore, the binding energy of the exciton is calculated numerically for arbitrary wire thicknesses, while the results of Ref. 8 were limited to thin wires. Finally, the addition of a magnetic field is another extension which hasn’t been studied before in detail. The effective potential was calculated before for embedded wires¹² for magnetic fields perpendicular and parallel to the wire axis. The techniques used in this paper are the same as in our paper, but in the paper the focus is not on the effective potential, it is on the calculation of the exciton energy and comparison with the experiment. For high magnetic fields the analytical expressions as obtained for parabolic confinement¹³, can be accurately fitted to our results. Note that our calculations are very general, since they apply to arbitrary materials if they can be described within the framework of the effective mass theory.

This paper is organized as follows. In Sect. II we consider the single particle states of the electron and hole. In Sect. III we calculate the effective potential of the exciton, using the adiabatic approximation. The numerical results for the effective potential as function of the inter particle distance are fitted to simple analytical expressions. The exciton energy is calculated numerically and semi-analytically in Sect. IV. The influence of a magnetic field will be investigated in Sect. V and our conclusions are presented in Sect. VI.

II. SINGLE PARTICLE STATES

For completeness we first consider the eigenfunctions and corresponding eigenvalues of a single particle in a circular¹⁴ potential well with radius R . Adopting the effective mass approximation we write the Schrödinger equation as follows:

$$-\frac{\hbar^2}{2m}\vec{\nabla}^2\psi(\vec{r}) + V(\vec{r})\psi(\vec{r}) = E\psi(\vec{r}), \quad (1)$$

where we approximate the confinement potential of the wire by a hard wall potential

$$V(\vec{r}) = \begin{cases} 0 & \text{if } \rho \leq R \\ \infty & \text{if } \rho > R \end{cases}, \quad (2)$$

where $\rho = \sqrt{x^2 + y^2}$. For the freestanding wire the potential height is given by the work function which is typically a few eV and therefore very large compared to typical confinement energies. The wire is oriented along the z -axis. Since the motion in the z -direction (free particle in that direction) is decoupled from the motion in the (x, y) -plane and because of circular symmetry, we have $\psi(\rho, \theta, z) = F(\rho)e^{-il\theta}e^{ik_z z}$, where θ is the polar angle. The Schrödinger equation is then reduced to the one dimensional (1D) equation

$$\rho^2 F(\rho)'' + \rho F(\rho)' + ((k^2 - k_z^2)\rho^2 - l^2)F(\rho) = 0, \quad (3)$$

with $k^2 = 2mE/\hbar^2$. The solution to this equation are the well known Bessel functions and taking hard wall boundary conditions into account, one gets for the single particle wave functions

$$\psi_{n,l,k_z}(\rho, \theta, z) = C_{n,l}e^{-il\theta}J_l\left(\frac{\beta_{n,l}}{R}\rho\right)e^{ik_z z}, \quad (4)$$

and the corresponding eigenenergies

$$E_{n,l,k_z} = \frac{\hbar^2\beta_{n,l}^2}{2mR^2} + \frac{\hbar^2k_z^2}{2m}, \quad (5)$$

where $C_{n,l}$ is the normalisation constant and $\beta_{n,l}$ is the n^{th} order zero of the Bessel function $J_l(x)$. The zeros of the Bessel functions are known and can be found in the literature¹⁵: $\beta_{0,0} = 2.4048, \beta_{0,1} = 3.8317, \beta_{0,2} = 5.1356, \beta_{1,0} = 5.5201, \beta_{1,2} = 8.4172, \beta_{2,2} = 11.6198, \dots$. Notice that the first excited state is $|0, 1, k_z\rangle$ and the second one $|0, 2, k_z\rangle$.

III. EFFECTIVE EXCITON POTENTIAL

A. Adiabatic approximation

The appropriate Hamiltonian for an exciton in the effective mass approximation is given by

$$H = -\frac{\hbar^2}{2m_e}\vec{\nabla}_e^2 + V_e(x_e, y_e) - \frac{\hbar^2}{2m_h}\vec{\nabla}_h^2 + V_h(x_h, y_h) + V_C(\vec{r}_e - \vec{r}_h), \quad (6)$$

where m_e (m_h) is the effective mass of the electron (hole), V_e (V_h) is the confinement potential of the electron (hole) and

$$V_C(\vec{r}_e - \vec{r}_h) = -\frac{1}{4\pi\epsilon}\frac{e^2}{\sqrt{(x_e - x_h)^2 + (y_e - y_h)^2 + (z_e - z_h)^2}}, \quad (7)$$

is the Coulomb interaction potential between the electron and the hole. In this case, it is convenient to separate the motion of the two particles into that of the center of mass of the system and the relative motion, thereby introducing the quantities: $Z = (m_e z_e + m_h z_h)/(m_e + m_h)$, $z = z_e - z_h$, $M = m_e + m_h$, $\mu = (m_e m_h)/(m_e + m_h)$. Now the Hamiltonian can be rewritten as

$$H = -\frac{\hbar^2}{2m_e}\vec{\nabla}_{x_e, y_e}^2 + V_e(x_e, y_e) - \frac{\hbar^2}{2m_h}\vec{\nabla}_{x_h, y_h}^2 + V_h(x_h, y_h) - \frac{\hbar^2}{2M}\frac{\partial^2}{\partial^2 Z} - \frac{\hbar^2}{2\mu}\frac{\partial^2}{\partial^2 z} - \frac{1}{4\pi\epsilon}\frac{e^2}{\sqrt{(x_e - x_h)^2 + (y_e - y_h)^2 + z^2}}. \quad (8)$$

In the case of strong lateral confinement, the exciton motion along the wire is decoupled from the lateral motion of the particles and we may decouple the wave function as follows

$$\Psi(x_e, y_e, x_h, y_h, z, Z) = e^{iKZ}\phi(z)\psi(x_e, y_e)\psi(x_h, y_h). \quad (9)$$

Because the Coulomb energy in the considered case is much weaker than the single particle confinement energy, we adopt the adiabatic approximation, thereby taking $\psi(x, y)$ as the above obtained single particle states. Multiplying Eq. (8) with $\psi^*(x_e, y_e)\psi^*(x_h, y_h)$ from the left and with $\psi(x_e, y_e)\psi(x_h, y_h)$ from the right, integrating over the lateral coordinates we reduce the original 6D Schrödinger equation for the exciton problem to a 1D effective Schrödinger equation for the relative exciton coordinate

$$\left(E_e + E_h + \frac{\hbar^2 K^2}{2M} - \frac{\hbar^2}{2\mu}\nabla_z^2 + V_{\text{eff}}(z)\right)\phi(z) = E_{\text{tot}}\phi(z), \quad (10)$$

where E_e (E_h) are the single-electron (hole) energies, and the effective exciton potential, V_{eff} , is given by

FIG. 1: Effective exciton interaction potential as a function of the electron-hole separation z for three different states of the electron and hole (Full curve: $n_e = l_e = 0$ and $n_h = l_h = 0$ for the hole; dashed curve: $l_e = l_h = 1$ and $n_e = n_h = 0$; dotted curve: $l_e = l_h = 2$ and $n_e = n_h = 0$). The regular Coulomb potential, $1/z$, is also plotted (dashed-dotted) for comparison. Inset: The effective potential for different sets of quantum numbers for the electron and hole.

FIG. 2: Density for the electron and hole in the nanowire for the lowest three single-particle states.

$$V_{\text{eff}}^{n,l}(z) = -\frac{e^2}{4\pi\epsilon} \iiint dx_e dx_h dy_e dy_h \times \frac{|\psi_{n,l,k_z}(x_e, y_e)|^2 |\psi_{n,l,k_z}(x_h, y_h)|^2}{\sqrt{(x_e - x_h)^2 + (y_e - y_h)^2 + z^2}}. \quad (11)$$

Introducing dimensionless units (i.e. length expressed in units of R) and $\alpha = a_B^*/2R$ with $a_B^* = 4\pi\epsilon\hbar^2/\mu e^2$ the effective Bohr radius, we finally get

$$(-\alpha\nabla_z^2 + \tilde{V}_{\text{eff}}(z))\phi(z) = \tilde{E}_C\phi(z), \quad (12)$$

where z is given in units of R , $\tilde{V} = V/E_0$, $\tilde{E}_C = E_C/E_0$, $E_0 = e^2/4\pi\epsilon R$ and $E_C = E_{\text{tot}} - E_e - E_h - \hbar^2 K^2/2M$. To study the bound energy states of the exciton, we first have to determine the exciton potential. Examining Eq. (11), it is clear that evaluating this integral numerically is not straight-forward because of the $1/r$ singularity for $r \rightarrow 0$.

The method we used to get rid of this problem, is explained in Appendix A. The result of the calculations can be found in Fig. 1, where we show the effective Coulomb potential when the electron and the hole are in the ground state, i.e. $\psi \rightarrow \psi_{0,0}$ ($V^{0,0}$) and in both the first and second excited state, i.e. $\psi \rightarrow \psi_{0,1}$ ($V^{0,1}$) and $\psi \rightarrow \psi_{0,2}$ ($V^{0,2}$) respectively (the single particle densities are shown in Fig. 2). Notice how all effective potentials in Fig. 1 show the $-1/z$ behaviour for $z \rightarrow \infty$ and that the effective potential is finite for $z = 0$.

B. Approximate analytical expressions

Since the calculation of the effective Coulomb potential requires a considerable amount of computational time, it is highly desirable to have an analytical expression for it. Let us first consider the small z behaviour of the effective potential:

$$\tilde{V}_{\text{eff}}(z) = a + bz + cz^2, \quad (13)$$

FIG. 3: Plot of the numerical data and the two Padé approximations, $P_0(z)/P_1(z)$ and $P_1(z)/P_2(z)$, for (a) the ground state and (b) the first and second (inset) excited state.

where $\tilde{V}_{\text{eff}}(z) = V_{\text{eff}}(z)/E_0$ and z is in units of R . The coefficients are given by

$$a = \tilde{V}_{\text{eff}}(z=0) = -2.5961, \quad (14a)$$

$$b = \left. \frac{d\tilde{V}_{\text{eff}}(z)}{dz} \right|_{z=0} = 4.1967, \quad (14b)$$

$$c = \left. \frac{1}{2} \frac{d^2\tilde{V}_{\text{eff}}(z)}{dz^2} \right|_{z=0} = -5.6140, \quad (14c)$$

for the single particle ground state. In a similar way, we get $a = -2.1126$ ($a = -1.9774$), $b = 3.1031$ ($b = 3.0608$) and $c = -4.5503$ ($c = -5.4277$) for the first (second) excited state. This polynomial expression, Eq. (13), is within 1 % of the numerical result for $z/R < 0.14$.

Next we will look for an analytical expression that fits the whole range of z -values. Therefore, we have approximated the full effective potential by Padé approximants. The first Padé approximation is given by

$$\tilde{V}_{\text{eff}}(z) = \frac{P_0(z)}{P_1(z)} = \frac{v}{w + |z|}, \quad (15)$$

where $P_i(z)$ is a polynomial of i -th order. If we take into account that $\tilde{V}_{\text{eff}}(0) = v/w$ and remember that for $z \rightarrow \infty$ the effective potential behaves as a normal Coulomb potential ($-1/z$), we can conclude that $v = -1$ and calculate that $w = 0.3852$ (ground state), $w = 0.4734$ (first excited state) and $w = 0.5057$ (second excited state).

This Padé approximation and the result of the calculations are compared in Fig. 3(a) for the ground state and Fig. 3(b) for the first and second excited state.

To improve this result we consider the next Padé approximation:

$$\tilde{V}_{\text{eff}}(z) = \frac{P_1(z)}{P_2(z)} = \frac{\gamma|z| + \delta}{z^2 + \eta|z| + \beta}. \quad (16)$$

Again, there are certain conditions which impose restrictions to the values of the parameters. These conditions are $\tilde{V}_{\text{eff}}(z) \xrightarrow{z \rightarrow \infty} -1/z$, which implies that $\gamma = -1$ and $\delta/\beta = \tilde{V}_{\text{eff}}(z=0)$, which leaves us with two fitting parameters. After fitting the data to the expression in Eq. (16), we find $\eta = 1.1288 \pm 0.0029$, $\beta = 0.4705 \pm 0.0015$, $\delta = -1.2215 \pm 0.0039$ for the electron and hole in the ground state,

FIG. 4: Comparison between the numerical effective electron-hole potential and the approximate one using the wave function of a harmonic oscillator for three different sets of quantum numbers of electron and hole.

$\eta = 1.728 \pm 0.017$, $\beta = 0.899 \pm 0.011$, $\delta = 1.900 \pm 0.023$ for the electron and hole in the first excited state and $\eta = 2.749 \pm 0.061$, $\beta = 1.559 \pm 0.039$, $\delta = -1.9774\beta = 3.083 \pm 0.077$ for the electron and hole in the second excited state. The fitted second Padé approximation is also shown in Fig. 3 and we obtain an excellent fit (i.e. within 1.5%) for all states.

If the confinement potential for the electron and hole is a parabolic potential, i.e. $V(x, y) = m\omega_0^2(x^2 + y^2)$, it is possible to perform all integrals in Eq. (11) analytically. The analytical result for the effective potential was obtained in Ref. 13 and reads

$$\tilde{V}_{\text{eff}}(z) = -\left(\frac{\pi}{2}\right)^{1/2} \frac{1}{l_0/R} \left[1 - \text{erf}\left(\frac{|z|}{\sqrt{2}l_0/R}\right) \right] e^{|z|^2/2(l_0/R)^2} \quad (17)$$

with the oscillator length $l_0 = (\hbar/m\omega_0)^{1/2}$. It is remarkable that this potential approaches our effective exciton potential very closely if we define l_0 to be

$$l_0/R = -\frac{1}{\tilde{V}_{\text{eff}}(0)} \left(\frac{\pi}{2}\right)^{1/2}. \quad (18)$$

i.e. the expression for the oscillator length extracted from Eq. (17) by putting $z = 0$. It is possible now to calculate numerically l_0/R for the different effective potentials: $l_0/R = 0.4828$ (ground state), $l_0/R = 0.5933$ (first excited state) and $l_0/R = 0.6338$ (second excited state). Using these results in Eq. (17), we get an expression for the effective exciton potential as function of the interparticle distance. The approximation and the calculated data can be seen in Fig. 4 and show a good agreement for ground state and first excited state (fit within 0.7% of the data), while for the second excited state the approximated result is still reasonable (fits within 3.2% of the data).

IV. EXCITON ENERGY

A. Numerical calculations

When a single exciton is created by excitation, its energy is generally given by $E = E_g + E_e + E_h + E_C$, where E_g denotes the energy band gap, $E_{e(h)}$ is the single electron (hole) energy and E_C is the (negative) energy of the Coulomb interaction between electron and hole. For a given material, we have to calculate now E_C , all other contributions to the exciton energy are known. Therefore, the 1D Schrödinger equation [Eq. (12)] was solved

FIG. 5: Binding energy as a function of the parameter $\alpha = a_B^*/2R$. The solid curves are calculated by using the effective potential $V^{0,0}$ (electron and hole in the ground state). The symbols represent the fit which is given by Eq. (19). Inset: The same, but now for the effective potential $V^{0,1}$ (electron and hole in the first excited state).

using the finite difference technique. Fig. 5 shows the energy of the Coulomb interaction of the three lowest exciton energy levels as a function of the dimensionless parameter $\alpha = a_B^*/2R$ for two cases of the effective potential.

The binding energy can also be fitted to an analytical expression now. Values of $\alpha < 0.1$ are not realistic, since this would correspond to a large radius and a strong confinement approach would no longer be valid. Therefore, the following fit is suggested for α values exceeding 0.1,

$$\tilde{E}_C = \frac{\xi}{1 + b\alpha^\tau}. \quad (19)$$

For the ground state configuration of the electron and hole, we find that $\xi = -2.145 \pm 0.020$, $b = -1.093 \pm 0.022$, $\tau = 0.5385 \pm 0.0040$, and for the first (second) excited states of the exciton binding energy we find $\xi = -1.287 \pm 0.031$, $b = 5.42 \pm 0.16$ and $\tau = 0.945 \pm 0.013$ ($\xi = -1.211 \pm 0.016$, $b = 10.23 \pm 0.14$ and $\tau = 0.8830 \pm 0.0034$) (see Fig. 5 for the fits). Similarly, for the configuration where electron and hole are in the first excited state, we find that $\xi = -1.714 \pm 0.015$, $b = -0.967 \pm 0.020$ and $\tau = 0.5449 \pm 0.0042$ (ground state), $\xi = -1.0525 \pm 0.028$, $b = 4.56 \pm 0.16$, $\tau = 0.940 \pm 0.016$ (first excited state) and $\xi = -0.965 \pm 0.016$, $b = 8.47 \pm 0.15$, $\tau = 0.8944 \pm 0.0051$ (second excited state).

From Eq. (12) it is clear that for small α -values, there is a relatively smaller contribution of the kinetic energy term $\nabla_z^2 \psi$. As α increases, the energy of the particle will also increase, because of an increase in the contribution from the kinetic energy term. For large values of α the energy levels become closely packed to the $\tilde{E}_C = 0$ level. In fact, because of the $1/z$ behaviour of the exciton potential for large z , the integral $\int V(z)^{1/2} dz = \infty$ and according to Ref. 16 there will be an infinite number of bound states.

B. Comparison with analytical results

In this section we present an analytical solution of the 1D Schrödinger equation Eq. (12). Similar calculations were done earlier by Loudon¹⁷, who solved the problem of the 1D hydrogen atom (i.e. the ideal limit of the 1D electron-hole system: infinitesimal wire cross-section and hard wall confinement) analytically. To avoid the divergence of the original potential at $z = 0$ Loudon used

FIG. 6: Ground state (lower curves) and first excited state (upper curves) energy of the exciton when 1) using the first Padé approximation for the electron-hole interaction potential and 2) the numerical expression for the electron and hole in the ground state. The curve with symbols is the asymptotic behaviour, i.e. Eq. (23).

different models, e.g. hard wall conditions at $z = 0$, i.e. $\phi(z = 0) = 0$. The 1D Schrödinger equation, Eq. (12), has in general to be solved numerically. We used the finite difference technique. In the special case in which the effective potential is approximated by the first Padé approximant, Eq. (15), it is possible to obtain an analytical expression for the wave function. After introducing the new variable $y = 2\sqrt{-\tilde{E}_C/\alpha}(z + w)$, we can rewrite Eq. (12) as the Whittaker equation:

$$\nabla_y^2 \phi(y) + \left(-\frac{1}{4} + \frac{-v}{2y\alpha\sqrt{-\tilde{E}_C/\alpha}} \right) \phi(y) = 0. \quad (20)$$

The wave functions are then given in terms of the Whittaker function

$$\phi(y) = Aye^{-y/2}U(1 - \kappa; 2; y), \quad (21)$$

where A is a normalisation constant and $\kappa = -v/2\alpha\sqrt{-\tilde{E}_C/\alpha}$. The energy is then obtained by solving the following equations:

$$\begin{aligned} \left. \frac{d\phi(y)}{dy} \right|_{y=2w\sqrt{-\tilde{E}_C/\alpha}} &= 0 \quad (\text{even states}), \\ \phi(y=2w\sqrt{-\tilde{E}_C/\alpha}) &= 0 \quad (\text{odd states}). \end{aligned} \quad (22)$$

We now obtain the energy of the Coulomb interaction semi-analytically (by solving the transcendent equation) and we compare it in Fig. 6 with the numerically calculated energy. Notice that for large α both energies are close to each other. But for small α -values (which corresponds to large R) there is a underestimation of the exciton energy up to 15 %. This is not surprising, since the first Padé approximation leads to a rather poor fit to the effective potential (see Fig. 3(a)). Nevertheless analytical calculations are useful because they allow for an estimation of the energy without having to solve the differential equation (12) numerically. Furthermore it has to be noticed that, in the case of large α (which corresponds to small radii R), it is now possible to find a simple analytical expression⁸ for $\tilde{E}_C$, i.e.

$$\tilde{E}_C = -1/4\alpha v^2 \quad (23)$$

where

$$\nu = \nu_m \begin{cases} \nu_m = m + \frac{w}{\alpha} & (\text{odd states}) \\ \nu_m = m - \frac{1}{\ln(w/m\alpha)} & (\text{even states}) \end{cases} \quad (24)$$

for $m = 1, 2, 3, \dots$. These correspond to the bound states of the exciton. This asymptotic result is shown in Fig. 6 by the square symbols and is clearly only valid for large α . Note that in the limit of a Coulomb interaction potential the excited states are twofold degenerate. The lowest bound state satisfies the special relation

$$\ln\left(\frac{w}{\nu_0\alpha}\right) + \frac{1}{2\nu_0} = 0. \quad (25)$$

This approximation is also shown in Fig. 6.

V. MAGNETIC FIELD DEPENDENCE

A. Single-particle properties

When a magnetic field, directed along the wire, is applied, the single-particle Hamiltonian for an electron ($q = -|e|$) or hole ($q = |e|$) can be written as

$$H = \frac{1}{2m} \left(-i\hbar\vec{\nabla} - q\vec{A} \right)^2 + V(\vec{r}), \quad (26)$$

where $V(\vec{r})$ is again the confinement potential of the wire. Due to the symmetry of the problem we may benefit from the symmetric gauge $\vec{A} = \frac{1}{2}B\rho\vec{e}_\theta$ for the vector potential. For the same reason, the wave function $\psi(\rho, \theta)$ is separable, and can be written as $\psi(\rho, \theta) = R(\rho)e^{-il\theta}$, where the z -dependence has been omitted for the sake of simplicity. The Schrödinger equation now reads

$$\begin{aligned} &\left(\frac{\partial^2}{\partial \rho^2} + \frac{1}{\rho} \frac{\partial}{\partial \rho} - \frac{l^2}{\rho^2} \right) R + \\ &\left(-\frac{m\omega_c}{\hbar} \text{sgn}(q)l - \left(\frac{m\omega_c}{2\hbar} \right)^2 \rho^2 + \frac{2mE}{\hbar^2} \right) R = 0 \end{aligned} \quad (27)$$

where $\omega_c = |e|\hbar B/m$ is the cyclotron frequency. Introducing the following parameters, $k^{*2} = -\text{sgn}(q)lm\omega_c/\hbar + 2mE/\hbar^2$ and $1/l_B^2 = m\omega_c/2\hbar$, and by putting $R(\rho) = \rho^{|l|} \exp(-\rho^2/2l_B^2)f(\rho)$, one gets

$$tf'' + ((|l|+1)-t)f' - \left(\frac{1}{2}(|l|+1) - \frac{l_B^2 k^{*2}}{4} \right) f = 0, \quad (28)$$

where the new variable t is given by $t = \rho^2/l_B^2$. The solution is the confluent hypergeometric function¹⁸.

$$\psi_{n,l}(\rho, \theta) = C_{n,l} e^{-il\theta} \rho^{|l|} e^{-\frac{\rho^2}{2l_B^2}} {}_1F_1 \left(-a_{n,l}; |l|+1; \frac{\rho^2}{l_B^2} \right), \quad (29)$$

FIG. 7: Effective exciton potential for different values of the magnetic field (full lines) in which the electron and hole are in the ground state. The approximation (open symbols) of Eq. (17) can be used again to fit the calculated effective potential. For comparison, the effective potential for the system without magnetic field was also drawn ($l_B/R = \infty$, dotted line). Note that for this figure, the electron and hole were in the ground state.

where $C_{n,l}$ is a normalisation constant and

$$-a_{n,l} = \frac{1}{2}(|l| + 1) - \frac{l_B^2 k^{*2}}{4}, \quad (30)$$

is a constant which is obtained by using the hard wall boundary conditions, i.e. $\psi_{n,l}(R, \theta) = 0$. The single particle energy then becomes

$$E_{n,l} = \hbar\omega_c \left(a_{n,l} + \frac{1 + |l| + \text{sgn}(q)l}{2} \right). \quad (31)$$

B. Effective exciton potential

The total Hamiltonian is now given by

$$\begin{aligned} H_{tot} = & -\frac{1}{2m_e} \left(\vec{p}_{x_e, y_e} + |e| \vec{A} \right)^2 + V_e(x_e, y_e) \\ & -\frac{1}{2m_h} \left(\vec{p}_{x_h, y_h} - |e| \vec{A} \right)^2 + V_h(x_h, y_h) \\ & -\frac{\hbar^2}{2m_e} \nabla_{z_e}^2 - \frac{\hbar^2}{2m_h} \nabla_{z_h}^2 \\ & -\frac{1}{4\pi\epsilon} \frac{e^2}{\sqrt{(x_e - x_h)^2 + (y_e - y_h)^2 + z^2}} \end{aligned} \quad (32)$$

Again, we can reduce this equation to a 1D effective Schrödinger equation similarly as for the $B = 0$ case by: i) separating the motion of the two particles into the center of mass relative coordinates, ii) by using the adiabatic approximation for the exciton wave function, and iii) by introducing the same dimensionless units as in Sect. III A. This leads us to the equivalent of Eq. (12), where the single particle energies are now given by Eq. (31) and the averaging of the effective potential has to be performed with the Kummer functions [Eq. (29)] (instead of Bessel functions). Note that the confluent hypergeometric function ${}_1F_1$ is equivalent to the Kummer function M :

$${}_1F_1(a; b; z) = M(a, b, z). \quad (33)$$

Fig. 7 shows the effective potential for different values of the magnetic field (which corresponds to different values of the magnetic length $l_B = \sqrt{2\hbar/m\omega_c}$). These potentials can be approximated again by the expression in Eq. (17) (see fit in Fig. 7). Therefore it is more

FIG. 8: Effective exciton potential at $z = 0$ as function of the magnetic length l_B (the magnetic field). The fit is to Eq. (35) and Eq. (37)

interesting to determine the relation between l_B and $\tilde{V}_{\text{eff}}(z = 0)$, since the value of $\tilde{V}(z = 0)$ will enable us to calculate l_0/R (Eq. (18)) and therefore to reconstruct the effective potential for the whole range of z -values for an arbitrary magnetic field. Fig. 8 shows this curve for both electron and hole in the ground state and in the first excited state.

This figure can be understood as follows. Large values of l_B correspond to the absence of a magnetic field and therefore the curve converges to the previously calculated value of $\tilde{V}_{\text{eff}, l_B \rightarrow \infty}(z = 0)$ for $B = 0$. For small values of l_B , Eq. (17) matches the calculated curve, because for high magnetic fields, the confinement becomes effectively parabolic. Replacing the oscillator length l_0 by l_B , the result for large magnetic fields is recovered:

$$\tilde{V}_{\text{eff}, l_B \rightarrow 0}^{0,0}(z = 0) = -\sqrt{\frac{\pi}{2}} \frac{1}{l_B/R} \quad (34)$$

Putting together these results into a single formula, we obtain a fit for the effective potential as function of the magnetic field:

$$\tilde{V}_{\text{eff}}^{0,0}(z = 0) = \tilde{V}_{\text{eff}, l_B \rightarrow \infty}^{0,0}(z = 0) - \sqrt{\frac{\pi}{2}} \frac{1}{\tilde{l}/R} e^{-p l_B}, \quad (35)$$

where $1/\tilde{l}^2 = 1/l_0^2 + 1/l_B^2$. Two parameters have been determined by fitting the data and are $l_0/R = 0.0624 \pm 0.0021$ and $pR = 8.570 \pm 0.090$ for the electron and the hole in the ground state configuration. Notice that basically we used the expression for the parabolic confinement Eq. (17) and by rescaling l_0 to $\tilde{l}$, we include the effect of the magnetic field.

By making a similar calculation to the one in Ref. 13, but for the electron and hole in the first excited state, we find that

$$\tilde{V}_{\text{eff}, l_B \rightarrow 0}^{0,1}(z = 0) = -\frac{11}{16} \sqrt{\frac{\pi}{2}} \frac{1}{l_B/R} \quad (36)$$

Therefore we fitted the data for $|n_e, l_e\rangle = |n_h, l_h\rangle = |n, l\rangle = |0, 1\rangle$ to a slightly different function,

$$\tilde{V}_{\text{eff}}^{0,1}(z = 0) = \tilde{V}_{\text{eff}, l_B \rightarrow \infty}^{0,1}(z = 0) - \frac{11}{16} \sqrt{\frac{\pi}{2}} \frac{1}{\tilde{l}/R} e^{-p l_B}, \quad (37)$$

where $l_0/R = 0.0462 \pm 0.0026$ and $pR = 10.73 \pm 0.17$. The numerical results together with the results of the fit are shown in Fig. 8 and agree very well.

FIG. 9: Ground state exciton binding energy for the electron and hole in the ground state as function of the magnetic length $l_B = \sqrt{2\hbar/eB}$ for different values of α . Inset: the same but now for the ground state, first and second excited state with $\alpha = 1$.

C. Exciton energy

Previously, we calculated the exciton energy as function of the dimensionless parameter $\alpha = a_B^*/2R$, which is determined by the wire radius and the material parameters. In this case, there is another variable which can be changed and will have an effect on the energy: the magnetic length l_B . Considering the previous results of the system without magnetic field and knowing that the shape of the potential does not fundamentally change by applying a magnetic field (the effective potential well only gets deeper), we know that also the energy as function of α will not give a fundamentally different result as before. Therefore we calculated the binding energy as function of the magnetic field (or the magnetic length l_B) for a few fixed values of α ($\alpha = 10$, $\alpha = 1$ and $\alpha = 0.1$) and the result of these calculations can be seen in Fig. 9. The main figure shows only the ground state binding energy, while the inset shows also the energy of the first and second excited state. The inset shows that the magnetic field influences the ground state more than the first and second excited states, which are almost constant. For high magnetic fields, which corresponds to $l_B/R \rightarrow 0$, we find that the effective potential of Eq. (17) becomes a $1/z$ -potential¹⁵. This means that we can use Eqs. (23)-(25) again to determine the asymptotic behaviour of $\tilde{E}_C$ as function of l_B . We find that the ground state energy $\tilde{E}_C \rightarrow \infty$ for $l_B \rightarrow 0$ for all values of α , whereas for $\alpha = 1$ (inset of Fig. 9) the first and second excited state become, in the limit $B \rightarrow \infty$ degenerate with energy $-1/4$.

VI. CONCLUSION

In summary we have calculated the effective interaction potential and the binding energy for an exciton in a nanowire. The effective interaction potential was calculated for different states of the electron and hole and we were able to present ‘exact’ numerical results. In order to reduce the amount of computational time for future calculations, these results were used to propose various analytical approximate expressions. We fitted the results to three different functions. A first Padé approximation gives the correct qualitative behaviour, but the fit was not optimal. Nevertheless this expression was useful to perform further analytical calculations to estimate the binding energy of the exciton, especially for small values of the wire radius R . A second Padé approximation as well as the result from the parabolic confinement resulted in very good fits. Furthermore the exciton binding energy was calculated both semi-analytically and numer-

ically and analytical approximations were given. We also investigated the influence of a magnetic field and determined an analytical expression for the effective potential for arbitrary magnetic field values. Finally we calculated the binding energy as a function of the magnetic field, where we found that the ground state binding energy is most affected by a variation of the magnetic field.

Acknowledgments

This work was supported by the Flemish Science Foundation (FWO-VI), the Belgian Science Policy, the EU network of excellence: SANDiE and the UA-IMEC, vzw collaborative project.

APPENDIX A: NUMERICAL CALCULATION OF THE EFFECTIVE POTENTIAL

To obtain the effective exciton potential of Eq. (11), we have to evaluate four-fold integrals. They can be rewritten in polar coordinates as follows, using the same dimensionless units as before:

$$V_{\text{eff}}(z) = -R^4 \iiint \rho_e \rho_h d\rho_e d\rho_h d\theta_e d\theta_h \times \frac{|\psi_{nl}(R\rho_e, \theta_e)|^2 |\psi_{n'l'}(R\rho_h, \theta_h)|^2}{\sqrt{\rho_e^2 + \rho_h^2 - 2\rho_e \rho_h \cos(\theta_e - \theta_h) + z^2}} \quad (\text{A1})$$

Due to cylindrical symmetry, we can perform the integral over the angle θ_h analytically, yielding

$$\int_0^{2\pi} d\theta_e \int_0^{2\pi} \frac{d\theta_h}{\sqrt{\rho_e^2 + \rho_h^2 - 2\rho_e \rho_h \cos(\theta_e - \theta_h) + z^2}} = 2\pi \frac{4}{\sqrt{(\rho_e + \rho_h)^2 + z^2}} \mathbb{K} \left(\frac{4\rho_e \rho_h}{(\rho_e + \rho_h)^2 + z^2} \right) \quad (\text{A2})$$

where $\mathbb{K}(m)$ is the elliptic integral of the first kind. Using a polynomial approximation¹⁵ for the elliptic integral,

$$\mathbb{K}(m) = \sum_{i=0}^4 a_i m_1^i + \sum_{i=0}^4 b_i m_1^i \ln \frac{1}{m_1} \equiv \mathbb{A}(m_1) + \mathbb{B}(m_1) \ln(1/m_1), \quad (\text{A3})$$

with $m_1 = 1 - m$, we find that

$$V_{\text{eff}}(z) = -2\pi R^4 \int_0^1 d\rho_e \rho_e |\psi_{nl}(R\rho_e, \theta_e)|^2 \times \underbrace{\int_0^1 4 \frac{d\rho_h \rho_h |\psi_{n'l'}(R\rho_h, \theta_h)|^2}{\sqrt{(\rho_e + \rho_h)^2 + z^2}} \left[\mathbb{A}(m_1) + \mathbb{B}(m_1) \ln \frac{1}{m_1} \right]}_{\equiv I_1}$$

In a next step, we calculate the integral I_1 over r_h using numerical techniques. To obtain good convergence, we

use the logarithmically weighted method and consider the following integral:

$$I(\rho_e, z) = \int_0^1 d\rho_h F(\rho_h, \rho_e, z) \ln \left(\frac{(\rho_e - \rho_h)^2 + z^2}{(\rho_e + \rho_h)^2 + z^2} \right). \quad (\text{A4})$$

We use the following transformation

$$I(\rho_e, z) = \sum_{i=0}^{s-1} \int_0^h dx F(x + hi, \rho_e, z) \times \ln \left(\frac{(x - (\rho_e - hi))^2 + z^2}{(x + (\rho_e + hi))^2 + z^2} \right), \quad (\text{A5})$$

where h denotes the step size and s the total number of steps. If we replace $F(x + hi)$ by $F_i + (F_{i+1} - F_i)x/h$, we can write (A5) as

$$I(\rho_e, z) = \sum_{i=0}^{s-1} F_i A_i(\rho_e, z) + (F_{i+1} - F_i) C_i(\rho_e, z), \quad (\text{A6}) \quad \text{with}$$

and the remaining problem is the calculation of the coefficients A_i and C_i . These coefficients are given by

$$A_i(\rho_e, z) = \int_0^h dx \ln \left(\frac{(x - (\rho_e - hi))^2 + z^2}{(x + (\rho_e + hi))^2 + z^2} \right),$$

$$C_i(\rho_e, z) = \frac{1}{h} \int_0^h dx x \ln \left(\frac{(x - (\rho_e - hi))^2 + z^2}{(x + (\rho_e + hi))^2 + z^2} \right). \quad (\text{A7})$$

These integrals can be performed analytically which leads to the following results:

$$A_i(\rho_e, z) = a(h - (\rho_e - hi)) - a(h + (\rho_e + hi)), \quad (\text{A8a})$$

$$C_i(\rho_e, z) = h^{-1} [c(h - (\rho_e - hi)) - c(h + (\rho_e + hi))] - 2r_e, \quad (\text{A8b})$$

$$a(y) = H_i(y) + H_i(h - y) + 2z \left[\arctan \left(\frac{y}{z} \right) + \arctan \left(\frac{h - y}{z} \right) \right],$$

$$H_i(y) = y \ln(y^2 + z^2),$$

$$c(y) = \frac{1}{2} (y(2h - y) + z^2) G_i(y) + \frac{1}{2} ((h - y)^2 - z^2) G_i(h - y) 2z(h - y) \left[\arctan \left(\frac{y}{z} \right) + \arctan \left(\frac{h - y}{z} \right) \right],$$

$$G_i(y) = \ln(y^2 + z^2). \quad (\text{A9})$$

Now we can write, using the logarithmically weighted method,

where

$$I_1 = \int \frac{4d\rho_h \rho_h |\psi_{n'l'}(R\rho_h, \theta_h)|^2}{\sqrt{(\rho_e + \rho_h)^2 + z^2}} (\mathbb{A}(m_1) + \mathbb{B}(m_1) \ln(m_1))$$

$$= \sum_{i=0}^{s-1} \int_0^h dx F(x + hi) (\mathbb{A}(m_1) + \mathbb{B}(m_1) \ln(m_1))$$

$$= \sum_{i=1}^{s-1} (F_i h \mathbb{A}(m_1) + F_i (A_i + C_{i-1} - C_i) \mathbb{B}(m_1))$$

$$+ F_s \frac{h}{2} \mathbb{A}(m_1) + F_s C_{s-1} \mathbb{B}(m_1), \quad (\text{A10})$$

$$F_i \equiv F(hi) = \frac{4hi |\psi_{n'l'}(Rhi, \theta_h)|^2}{\sqrt{(\rho_e + hi)^2 + z^2}}. \quad (\text{A11})$$

The final step is to calculate then the integral over ρ_e . Similarly, we can also perform this last integration over ρ_e . Using the above mentioned result of Eq. (A10), we obtain the final expression for the effective potential in the z -direction:

$$V_{\text{eff}}(z) = -\frac{2\pi}{N^2} R^4 \left[h \sum_{j=1}^{s-1} hj |\psi_{nl}(Rhj, \theta_e)|^2 \left[[S_1(hj)h + T(hj)\frac{h}{2} \mathbb{A}(m_1)] - [S_2(hj) + T(hj)C_{s-1} \mathbb{B}(m_1)] \right] \right.$$

$$\left. + \frac{h}{2} hs |\psi_{nl}(Rsh, \theta_e)|^2 \left[[S_1(hs)h + T(hs)\frac{h}{2} \mathbb{A}(m_1)] - [S_2(hs) + T(hs)C_{s-1} \mathbb{B}(m_1)] \right] \right]$$

with

$$S_1(x) = \sum_{i=1}^{s-1} \frac{4hi |\psi_{n'l'}(Rhi, \theta_h)|^2}{\sqrt{(x+hi)^2 + z^2}} \mathbb{A}(m_1), \quad (\text{A12})$$

$$T(x) = \frac{4sh |\psi_{n'l'}(Rsh, \theta_h)|^2}{\sqrt{(x+sh)^2 + z^2}}, \quad (\text{A13})$$

$$S_2(x) = \sum_{i=1}^{s-1} \frac{4hi |\psi_{n'l'}(Rhi, \theta_h)|^2}{\sqrt{(x+hi)^2 + z^2}} (A_i + C_{i-1} - C_i) \mathbb{B}(m_1). \quad (\text{A14})$$

- * Electronic address: an.slachmuylders@ua.ac.be
† Electronic address: bart.partoens@ua.ac.be
‡ Electronic address: wim.magnus@imec.be
§ Electronic address: francois.peeters@ua.ac.be
- ¹ A.M. Morales and C.M. Lieber, Science **279**, 208 (1998).
 - ² X. Duan, Y. Huang, Y. Cui, and C.M. Lieber, Nano Lett. **2**, 101 (2002).
 - ³ Y. Cui and C.M. Lieber, Science **291**, 851 (2001).
 - ⁴ X. Duan, Y. Huang, and C.M. Lieber, Nano Lett. **2**, 487 (2002).
 - ⁵ M.H. Huang, S. Mao, H. Feick, H. Yan, Y. Wu, E. Weber, R. Russo, and P. Yang, Science **292**, 1897 (2001).
 - ⁶ X. Duan, Y. Huang, R. Agarwal, and C.M. Lieber, Nature (London) **421**, 241 (2003).
 - ⁷ Y. Cui, Q. Wei, H. Park, and C.M. Lieber, Science **293**, 1289 (2001).
 - ⁸ T. Ogawa and T. Takagahara, Phys. Rev. B **44**, 8138 (1991).
 - ⁹ D.S. Chu, C.M. Hsiao, and W.N. Mei, Phys. Rev. B **46**, 3898 (1992).
 - ¹⁰ S.V. Brans, G. Li, and K.K. Bajaj, Phys. Rev. B **47**, 1316 (1993).
 - ¹¹ L. Banyai, I. Galbraith, C. Ell, and H. Haug, Phys. Rev. B **36**, 6099 (1987). Note that this paper contains several mistakes in the formulas; the figures, however, are correct which indicates that mistakes are typing errors. Nevertheless, one should be careful and not just copy the formulas.
 - ¹² Y. Sidor, B. Partoens, and F.M. Peeters, Phys. Rev. B **71**, 165323 (2005).
 - ¹³ S. Bednarek, B. Szafran, T. Chwiej, and J. Adamowski, Phys. Rev. B **68**, 045328 (2003).
 - ¹⁴ For the sake of simplicity, we took circular symmetry. One can perform similar calculations for square wires and find that the final results, i.e. the effective exciton potential and exciton energy, match the result of a circular wire with radius comparable to half of the side of a square. This was investigated by Y. Zhang, and A. Mascarenhas, Phys. Rev. B **59**, 2040 (1999).
 - ¹⁵ M. Abramowitz and I. Stegun, *Handbook of mathematical functions* (Dover, New York, 1970), pp. 295, 409, 590.
 - ¹⁶ P.J. Price, Sol. State Electron. **39**, 653 (1996).
 - ¹⁷ R. Loudon, Am. J. Phys. **27**, 649 (1959).
 - ¹⁸ F. Geerinckx, F.M. Peeters, and J.T. Devreese, J. Appl. Phys. **68**, 3435 (1990).

This figure "Fig1.png" is available in "png" format from:

<http://arXiv.org/ps/cond-mat/0512385v1>

This figure "Fig2.png" is available in "png" format from:

<http://arXiv.org/ps/cond-mat/0512385v1>

This figure "Fig3.png" is available in "png" format from:

<http://arXiv.org/ps/cond-mat/0512385v1>

This figure "Fig4.png" is available in "png" format from:

<http://arXiv.org/ps/cond-mat/0512385v1>

This figure "Fig5.png" is available in "png" format from:

<http://arXiv.org/ps/cond-mat/0512385v1>

This figure "Fig6.png" is available in "png" format from:

<http://arXiv.org/ps/cond-mat/0512385v1>

This figure "Fig7.png" is available in "png" format from:

<http://arXiv.org/ps/cond-mat/0512385v1>

This figure "Fig8.png" is available in "png" format from:

<http://arXiv.org/ps/cond-mat/0512385v1>

This figure "Fig9.png" is available in "png" format from:

<http://arXiv.org/ps/cond-mat/0512385v1>